



### **TERM OF WARRANTY**

The plates of plywood plasticized F.V. de Araujo, are made after a stringent selection of raw materials throughout the monitoring process with high reliability to the product.

The plates of plywood plasticized F.V. de Araujo, have guaranteed the use of 30 uses and 15 uses for each face.

For this warranty to be valid and that the customer gets a better performance of plywood plasticized F.V. de Araujo, some cautions are needed regarding the handling and storage of plates.

### **HANDLING AND STORAGE**

After receipting and verification of plasticized plates F.V. de Araujo, the customer must prepare them in an appropriate place, transportation careful with the edges, corners and surfaces of the plates and should be protected to avoid damaged and changing the initial characteristics and dimensional quality of the product.

Before each use and reuse of the plates is recommended the application of release agent on the surfaces of plates, after the first use of the plates should be cleaned with water under controlled pressure and / or damp, wooden or plastic, to avoid any object metal or blunt to avoid damage which could compromise the quality and warranty the plates of plywood plasticized F.V de Araujo, after these procedures apply again the release agent, and so repeat the process for each use of the plates.

If the plate require special cutting the client should take special precautions regarding the type of saw used and bench, we recommend saw videa at least 96 teeth (120 teeth ideal), with an average diameter of 350 mm and a minimum rotation recommended 3800 rpm.

During the setting of nails and / or screws or other accessories are recommended to be done in a minimum distance of 3 to 4 cm from the ends of the plates to avoid damage to the structure of the plate, it is not advisable to use nails and / or screws the tops of the plates of plywood plasticized F.V de Araujo.

The plates of plywood plasticized F.V de Araujo, leaving the production process with all edges sealed with suitable paint, so when cut or pierced by nails or screws or other holes should be sealed to maintain the sealing of the plates.

We recommend the use of levers and wedges of wood during the removal of the plates for reuse, it is recommended to prevent crowbars and other materials that may damage the plates.

If you use vibrators should not be touching the surfaces of the plates during the concreting and preferably use vibrators with tips coated with rubber to avoid damaging the surfaces of the plates.

The plates of plywood plasticized F.V de Araujo, should be cleaned before being stored after use as described above and packed properly.

Stacking the plates must be done in a balanced way, in horizontally with at least three props and distributed to the full extent of the plates with a minimum distance of 10 cm from the floor, avoiding curvatures in the plates.

When storage is made over an extended time, should preferably be in a covered, dry and airy, where not exposed to rain, sun and moisture for the life of the plates is not compromised its performance and give the customer total satisfaction.

F.V. de Araujo S.A.  
Comercial Department